

Spraying Instructions Mighty Brighty Projection Screen Paint

Before you begin:

- 1. Carefully read the following chapters in the instruction booklet: Before you begin:
 - The surroundings and temperature
 - The surface upon which Mighty Brighty will be applied
- 2. Cover the side-walls, floor and ceiling with paper or plastic sheets.
- 3. Remove or cover objects (e.g. chairs) with paper or plastic foil. Some overspray during spraying can adhere on the objects.

Recommended Equipment:

Undiluted

BaseCoat

We recommend using an electric airless type of pump; Graco 495 II (costs $\pm \in 3.100$) with spraying-angle of 60° and spraying-nozzle of min.0,015". Pressure appr. 200 bars. Maximum sprayer snake 16 mtr. Follow the instructions of the manufacturer.

Keep the gun at a constant distance (appr. 25 cm) from the wall. Release the trigger at the end of each stroke.

Then, depress the trigger and overlap the previous stroke by about 1/3. Continue for consistent coverage.

After drying (ca. 60 minutes) apply a second (cross-)layer of BaseCoat.

TopCoa

Follow the same procedure as for the BaseCoat. The recommended pressure will be 180 bars.

MIGHTY BRIGHTY

Manufactured by: Golden Care

Bosstraat 63a, 5553 CK Valkenswaard, The Netherlands Tel.: +31 40 2041115, E: info@mightybrighty.com

EXCLUSIVE DISTRIBUTOR EUROPE, MIDDLE EAST & AFRICA:

BMB ELECTRONICS BV

Kortakker 10 4264 AE Veen, The Netherlands Tel.: +31 416 315 710 Fax: +31 416 315 719

E: info@bmbelectronics.nl W: www.bmbelectronics.eu

Diluted

BaseCoat

Dilute BaseCoat with appr. 15 - 20 % water.

We recommend using the Graco 4900 Compression Turbine (costs $\pm \in 1.700$) in combination with a High Volume Low Pressure gun with a 2 mm tip diameter. Adjust the air/paint mixture in the optimal manner for consistent coverage using about 0,5 bars pressure. Follow the instructions of the manufacturer.

Keep the gun at a constant distance (appr. 15 cm) from the wall. Release the trigger at the end of each stroke.

Then, depress the trigger and overlap the previous stroke by about 1/3. Continue for consistent coverage.

After drying (ca. 60 minutes) apply a second (cross-)layer of BaseCoat.

TopCoat

TopCoat will **not** require dilution. Follow the same procedure as above for the BaseCoat.

Remark: In case of using a compressor in combination with HVLP guns, you will have to use compressors with high capacities (min. 500 ltr air/min.).

www.mightybrighty.com

Turn any wall into a projection screen